

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 2002-063949

(43)Date of publication of application : 28.02.2002

(51) Int. Cl.

H01M 14/00

H01L 31/04

(21)Application number : 2000-
246990

(71)Applicant : NATIONAL INSTITUTE OF
ADVANCED INDUSTRIAL &
TECHNOLOGY

(22)Date of filing : 16.08.2000 (72)Inventor : INOUE KOZO

BA ENREI

ABE HIDEKAZU

NOMA HIROAKI

(54) DYE SENSITIZED SOLAR BATTERY

(57)Abstract:

PROBLEM TO BE SOLVED: To provide a regeneration dye sensitized solar battery which can be practically used wherein porphyrin derivatives and their metal complexes are used and which has high photovoltaic conversion characteristics.

SOLUTION: In the solar battery in which an electrolyte is filled between a pair of electrodes wherein a transparent electroconductive film having a porous semiconductor film in an inner side surface is assumed as one side of electrodes and a metal film is assumed as the other side of electrodes and wherein a current circuit is formed between both electrodes by irradiate from the transparent electroconductive film side at least one kind of pigment selected from porphyrin compounds expressed in a formula (R is hydrogen atom or acid substituted group) and their metal complexes is carried in fine pores of porous semiconductor film.

CLAIMS

[Claim(s)]

[Claim 1] In a solar cell which uses as one electrode a transparent conducting film which has porosity semiconductor membrane in an inner surface inserts an electrolyte between electrode pairs which use a metal membrane as an electrode of another side irradiates with light from the transparent conducting film side and makes a current circuit form among two poles it is a general formula in fine pores of porosity semiconductor membrane. [Formula 1]

The dye-sensitized solar cell making at least one sort of coloring matter chosen from the porphyrin compounds expressed with (R in a formula is a hydrogen atom or acidic substituent) and those metal complexes support.

[Claim 2] The dye-sensitized solar cell according to claim 1 whose R in a general formula is a carboxyl group.

DETAILED DESCRIPTION

[Detailed Description of the Invention]

[0001]

[Field of the Invention] This invention has high photoelectric conversion efficiency and relates to the dye-sensitized solar cell which can supply photoelectric current stable moreover.

[0002]

[Description of the Prior Art] The type which a solar cell is a photoelectric cell with which the purpose of exploiting the energy of sunlight is presented and is used former most widely Pn junction is made to form near the surface with the large light-receiving surface of a semiconducting crystal or an amorphous board and the external circuit which irradiates with visible light and connects p field and n field is made to generate current toward n from p. As a semiconducting crystal in this case although many silicon is used the manufacturing process of silicon is an energy many consumption type intrinsically and since harmful silane gas is used a problem is also in respect of environmental protection and also there is a fault that a manufacturing cost is high.

[0003] By the way in 1991 gray TSUERU and others of Switzerland

(Graezel) The electrode which made the surface of the porosity titanium dioxide thin film with large surface area absorb ruthenium bipyridine carboxylic acid coloring matter is used Since the dye-sensitized solar

cell was announced and there have been the strong points such as that there is no fear of environmental pollution that a manufacturing cost is cheap and having high photoelectric conversion efficiency a reproduced type dye sensitizing photoelectric conversion cell has come to attract attention. However although what the chlorophyll derivative the zinc complex of porphyrin etc. made the optical-pumping center until now is proposed as this dye-sensitized solar cell these may be satisfied in order to present practical use as a solar cell since the photoelectric transfer characteristic is low.

[0004]

[Problem(s) to be Solved by the Invention] This invention is a basis of such a situation and is made for the purpose of providing the utilizable reproduced type dye-sensitized solar cell using the porphyrin derivatives which have a high photoelectric transfer characteristic and those metal complexes.

[0005]

[Means for Solving the Problem] A result of this invention persons having manufactured a metal complex of various porphyrin derivatives and having examined many things about the photosensitization operation New 510 and 1520 **TETORA phenylporphyrin or its derivative Or when that metal complex is used as coloring matter of a dye-sensitized solar cell it finds out that a solar cell which shows a high photoelectric transfer characteristic and can supply stable photoelectric current is obtained and came to make this invention based on this knowledge.

[0006] That is this invention is a general formula in fine pores of porosity semiconductor membrane in a solar cell which uses as one electrode a transparent conducting film which has porosity semiconductor membrane in an inner surface inserts an electrolyte between electrode pairs which use a metal membrane as an electrode of another side irradiates with light from the transparent conducting film side and makes a current circuit form among two poles. [Formula 2]

The dye-sensitized solar cell making at least one sort of coloring matter chosen from the porphyrin compounds expressed with (R in a formula is a hydrogen atom or acidic substituent) and those metal complexes support is provided.

[0007]

[Embodiment of the Invention] Next an embodiment of the invention is described according to an accompanying drawing. Drawing 1 is one example of the structure of this invention solar cell a sectional view for being

shown and between two glass substrates (the transparent substrate 1 and 7 for example glass substrates) The transparent conducting film 2 the porosity semiconductor membrane 3 the electrolyte 5 and the metal membrane 6 are arranged one by one and said semiconductor membrane 3 is formed in porosity and adsorption support of the porphyrin compound expressed with said general formula (I) in the fine pores or its metal complex is carried out. 8 is a current circuit and 9 is an ammeter.

[0008] As a material of the above-mentioned transparent electric conductor 2 the complex of the tin oxide and it and indium oxide is used for example. As a material of the semiconductor membrane 3 titanium oxide, zinc oxide, tantalum oxide etc. are used. This semiconductor membrane 3 needs to form as porosity. The semiconductor membrane which has such porosity semiconductor membrane on the surface For example journal physical chemistry (J. Phys. Chem.) the 94th volume and the method indicated to 8720 pages (1990) are referred to Melt titanium tetraisopropoxide in the mixture of 2-propanol, deionized water and nitric acid hydrolyze and a stable titanium oxide colloidal solution (particle diameter of about 8 nm) is prepared After mixing this solution with TiO_2 impalpable powder (the product made by Japanese Aerosil trade name "P-25") and a polyethylene glycol and carrying out spin coating of this mixture on semiconductor membrane it can manufacture by calcinating above 500 °C.

[0009] Next as a material of the metal membrane 6 used as a counter electrode although aluminum, tin, silver, copper etc. are used especially a desirable thing is platinum. This metal membrane 6 can form metal chemical vacuum deposition or by carrying out a physical vapor deposition for example on a glass substrate and other transparent substrates.

[0010] In this invention it is required to make at least one sort of coloring matter chosen from the porphyrin compound expressed with said general formula (I) in the fine pores of the aforementioned porosity semiconductor membrane 3 and its metal complex support. As a metal complex of this porphyrin compound it is a general formula for example.
[Formula 3]

The metal complex expressed with (a hydrogen atom or acidic substituent at least one sort of ligands as which X is chosen from an alkoxy group, an aryloxy group, an acyloxy group and a halogen atom and M of R in a formula are Mo, Cr, Nb or W) can be mentioned. General formula HX' (III) after making the carbonyl compound of Mo, Cr, Nb or W react to the porphyrin

compound which the metal complex expressed with this general formula (II) is a new molecular entity of literature non-******for example is expressed with said general formula (I) or its derivative

It can manufacture by processing with a compound expressed with (X' in a formula is an alkoxy group an aryloxy group an acyloxy group or a halogen atom) and processing by hydrogen halide further according to a request.

[0011] Although R in a porphyrin compound which is this general formula (I) or (II) and is expressed or its metal complex is a hydrogen atom or acidic substituent as this acidic substituent there are a carboxyl group sulfonic acid residues sulfonate residues sulfuric acid residues sulfate residue etc. for example. M is a metal atom which can form porphyrin and a complex. i.e. Mo Cr Nb or W.

[0012] X is a basis used as a ligand of M and Next a methoxy group an ethoxy basis a propoxy group There are an acyloxy group like an alkoxy group like a butoxy group a phenoxy group an aryloxy group like p ******MECHIRU phenoxy group an acetyloxy group a propionyloxy group and a glycol oxy group a fluorine atom a chlorine atom a halogen atom like a bromine atom etc.

[0013] A metal complex of a porphyrin compound expressed with said general formula (II) To a porphyrin compound like 510 1520 ******TETORA phenylporphyrin or 510 and 15 and 20 ******TETORA substituted phenyl porphyrin metal carbonyl For example molybdenum hexacarbonyl chromium pentacarbonyl niobium pentacarbonyl After making tungsten pentacarbonyl etc. react it can manufacture easily by making alcohol phenol and carboxylic acid contact contacting the output to hydrogen halide according to a request further and crystallizing. A reaction of this porphyrin compound and metal carbonyl can be performed using a solvent for example dimethylformamide according to a request. This reaction is advantageous at a point that go on in a short time of 30 minutes thru/or 2 hours in a room temperature a porphyrin metal complex is obtained with high yield of not less than 65% and moreover refining is also easy.

[0014] In order to make the porosity semiconductor membrane 3 support at least one sort of coloring matter 4 chosen from a porphyrin compound which is general formula (I) or (II) and is expressed and its metal complex After neglecting it until it dissolves this coloring matter in a suitable solvent for example dimethylformamide it carries out the dipping of the porosity semiconductor membrane into this solution and coloring matter fully adsorbs into fine pores of porosity semiconductor membrane this is taken out and it dries after washing if needed.

[0015] Next in this invention solar cell although platinum is preferred as a material of the metal membrane 6 used as a counter electrode a thing

publicly known as a counter electrode of the conventional solar cell such as the other aluminum, silver, tin and indium can also be used arbitrarily. As for these metal membranes 6 it is preferred to form a physical vapor deposition or by carrying out chemical vacuum deposition on a glass substrate or indium oxide and a tin-oxide complex board.

[0016] In this invention solar cell as an electrolyte inserted between two electrodes although conventionally used as an electrolyte of a solar cell it can choose from inside suitably and can use. An electrolyte used as such a thing with a solar cell using ruthenium bipyridine carboxylic acid coloring matter of gray TSUERO and others mentioned above for example that is there are some which dissolved iodine and potassium iodide in a medium which consists of a mixture of polypropylene carbonate 25 mass % and ethylene carbonate 75 mass %.

[0017] Thickness of the transparent conducting film 2 in this invention solar cell 0.4–0.6 micrometer. As for the particle size thickness of 0.01–0.03 micrometer and the metal membrane 6 is chosen in 10–15 micrometers in and 5–30 micrometers of thickness [0.01–0.06 micrometer of / 2–20 micrometers of] of 0.5 micrometer and the porosity semiconductor membrane 3 are preferably chosen in 10–12 micrometers. A range of 8–20 micrometers of thickness of an electrolyte inserted between two electrodes is 10–12 micrometers preferably.

[0018] If a solar cell of such a structure connects between two electrodes with a lead and makes a current circuit form and it irradiates with 420-nm white light from the transparent conducting film side it can be generated with high photoelectric conversion efficiency of not less than 2.9%. Since this photoelectric conversion efficiency is influenced by thickness of each film, a state of semiconductor membrane, the amount of adsorption of coloring matter, electrolytic kind, etc. it can be further raised by choosing these optimal conditions.

[0019]

[Example] Next an example explains this invention still in detail.

[0020] The mixture of the reference examples 151 and 150.5 g (0.6 mmol) of 20 **TETORA (4 **KARUBOKISHI phenyl) porphyrin 0.8 g (3.2 mmol) of molybdenum hexacarbonyl and 100 ml of dry dimethylformamide was refluxed under a nitrogen atmosphere for 2 hours. The stages of progress of the reaction were pursued with the ultraviolet visible spectrum in the meantime. Subsequently the solvent was distilled off after suspending heating and cooling a reaction mixture radiationally to a room temperature. Subsequently the glossy crystal was obtained with the yield of 67% by recrystallizing the solid of dark green obtained by carrying out ionic exchange column chromatography processing and refining a

residue in ethyl alcohol. An ultraviolet visible spectrum and infrared absorption spectrum, ESR ultimate analysis and when mass-spectrum analysis was conducted it was checked that it is a porphyrin metal complex (D) in which X in said general formula (II) corresponds to an ethoxy basis about this crystal M corresponds to Mo and R corresponds to the structure of a hydrogen atom. It processes similarly using 5101520 **TETORA phenylporphyrin or 510 and 15 and 20 **TETORA (4 **SURUHO phenyl) porphyrin as a raw material. The porphyrin metal complex (E) and (F) in which X in said general formula (II) corresponds to an ethoxy basis M corresponds to Mo and R corresponds to the structure of a carboxyl group or a sulfonic group was obtained.

[0021] Into 60 ml of hexane which saturated reference example 2 hydrogen chloride the solution which melted 50 ml of porphyrin metal complexes (E) obtained by the reference example 1 in 15 ml of ethyl alcohol was dropped at the room temperature. The generated crystal was ****(ed) with the glass filter and white crystals were obtained with the yield of 82% by drying after washing by hexane. It was checked that it is a porphyrin metal complex in which X [in / for this thing / said general formula (II)] corresponds to a chlorine atom an ultraviolet visible spectrum and infrared absorption spectrum, ESR ultimate analysis and when mass-spectrum analysis is conducted M corresponds to Mo and R corresponds to the structure of a carboxyl group.

[0022] Instead of the molybdenum hexacarbonyl in the reference example 3 reference example 1 chromium hexacarbonyl when it was made to react similarly using niobium hexacarbonyl or tungsten hexacarbonyl the porphyrin metal complex in which Cr Nb or W corresponds [M in general formula (II)] respectively was obtained.

[0023] After dissolving 62.5 ml of example 1 titanium tetraisopropoxide into 10 ml of 2-propanol and the mixture of 380 ml of deionized water and 3 ml of concentration 70 mass % nitric acid and making it hydrolyze in 80 ** for 8 hours evaporation concentration was carried out and the stable titanium oxide colloidal solution was prepared. The particle diameter of this titanium oxide was about 8 nm. As a result of carrying out an X diffraction it turned out that this titanium oxide is an anatase type. On the surface of the sheet metal (25x25 mm) of a 0.5-micrometer-thick indium oxide tin-oxide complex (henceforth [ITO]). The 10-micrometer-thick porous-titanium-oxide film was made to form by carrying out spin coating of the aforementioned colloidal solution 10 g and 2 g of TiO₂ impalpable powder (the product made by Japanese Aerosil trade name "P-25") and a mixture with 2 g of polyethylene glycols and calcinating them at 500 ** for 1 hour.

[0024] 5101520 **TETORA phenylporphyrin (A) 510 and 1520 **TETORA (4 **KARUBOKISHI phenyl) porphyrin (B) 5101520 **TETORA (4 **SURUHO phenyl) porphyrin (C) 5101520 **TETORA phenylporphyrin metal complex (D) which were obtained by the reference example 15101520 **TETORA (4 **KARUBOKISHI phenyl) porphyrin metal complex (E) and 510 and 15 and 20 **TETORA (4 **SURUHO phenyl) porphyrin metal complex (F) are dissolved in dimethylformamide with 5×10^{-4} molar concentration. After carrying out the dipping of the above-mentioned porous-titanium-oxide film into the prepared solution and neglecting it in 80 ** overnight it took out in argon atmosphere and washed and dried with methyl alcohol.

[0025] As a counter electrode using what provided platinum membrane (10 micrometers in thickness) by sputtering process on the ITO board (22x25 mm) as an electrolyte The solar cell of the structure which shows the iodine 0.38g and the mixture of 2.49 g of potassium iodide in drawing 1 using what was dissolved in the mixture 30g of propylene carbonate 25 mass % and ethylene carbonate 75 mass % was manufactured. Before long the performance of the solar cell of B and C was as follows.

[0026]

[Table 1]

[0027]

[Effect of the Invention] The dye-sensitized solar cell which can supply the photoelectric current which has high photoelectric conversion efficiency and was moreover stabilized by this invention is provided.

DESCRIPTION OF DRAWINGS

[Brief Description of the Drawings]

[Drawing 1] The sectional view showing one example of the structure of the solar cell of this invention.

[Description of Notations]

- 1 and 7 Transparent substrate
- 2 Transparent conducting film
- 3 Porosity semiconductor membrane
- 4 Coloring matter
- 5 Electrolyte
- 6 Metal membrane
- 8 Current circuit

9 Ammeter

(19) 日本国特許庁 (J P)

(12) 公 開 特 許 公 報 (A)

(11) 特許出願公開番号
特開2002-63949
(P2002-63949A)

(43) 公開日 平成14年2月28日 (2002.2.28)

(51) Int.Cl. ⁷	識別記号	F I	テームト* (参考)
H 0 1 M 14/00		H 0 1 M 14/00	P 5 F 0 5 1
H 0 1 L 31/04		H 0 1 L 31/04	Z 5 H 0 3 2

審査請求 有 請求項の数 2 O L (全 5 頁)

(21) 出願番号 特願2000-246990 (P2000-246990)

(22) 出願日 平成12年8月16日 (2000.8.16)

(71) 出願人 301021533

独立行政法人産業技術総合研究所
東京都千代田区霞が関1-3-1

(72) 発明者 井上 耕三

佐賀県鳥栖市宿町字野々下807番地1 工
業技術院九州工業技術研究所内

(72) 発明者 馬 廷麗

佐賀県鳥栖市宿町字野々下807番地1 工
業技術院九州工業技術研究所内

(74) 復代理人 100071825

弁理士 阿形 明

最終頁に続く


(54) 【発明の名称】 色素増感太陽電池

(57) 【要約】

【課題】 高い光電変換特性を有するポルフィリン誘導体とそれらの金属錯体を用いた、実用化可能な再生型色素増感太陽電池を提供する。

【解決手段】 多孔質半導体膜を内側表面に有する透明導電膜を一方の電極とし、金属膜を他方の電極とする電極対間に電解質を介挿し、透明導電膜側から光を照射して両極間に電流回路を形成させる太陽電池において、多孔質半導体膜の細孔中に、一般式

【化1】




(Rは水素原子又は酸性置換基) で表わされるポルフィリン化合物及びそれらの金属錯体の中から選ばれる少なくとも1種の色素を担持させる。

【特許請求の範囲】

【請求項 1】 多孔質半導体膜を内側表面に有する透明導電膜を一方の電極とし、金属膜を他方の電極とする電極対間に電解質を介挿し、透明導電膜側から光を照射して両極間に電流回路を形成させる太陽電池において、多孔質半導体膜の細孔中に、一般式

【化 1】



(式中の R は水素原子又は酸性置換基である) で表わされるポルフィリン化合物及びそれらの金属錯体の中から選ばれる少なくとも 1 種の色素を担持させたことを特徴とする色素増感太陽電池。

【請求項 2】 一般式中の R がカルボキシル基である請求項 1 記載の色素増感太陽電池。

【発明の詳細な説明】

【0001】

【発明の属する技術分野】 本発明は、高い光電変換効率を有し、しかも安定した光電流を供給することができる色素増感太陽電池に関するものである。

【0002】

【従来の技術】 太陽電池は、太陽光のエネルギーを利用する目的に供される光電池で、これまで最も広く用いられているタイプは、広い受光表面をもつ半導体結晶又はアモルファス板の表面付近に p n 接合を形成させ、可視光線を照射して p 領域と n 領域を連結する外部回路に p から n に向って電流を発生させるものである。この際の半導体結晶としては、ケイ素が多く用いられているが、ケイ素の製造工程は本質的にエネルギー多消費型であり、かつ有害なシランガスを用いているため、環境保全の面でも問題がある上に製造コストが高いという欠点がある。

【0003】 ところで、1991年にスイスのグレーツェル (G r a e z e l) らが、表面積の大きい多孔質二酸化チタン薄膜の表面にルテニウムビスピリジンカルボン酸色素を吸収させた電極を用いて、色素増感太陽電池を発表して以来、製造コストが安い、環境汚染のおそれがない、高い光電変換効率を有するなどの長所があることから、再生型色素増感光電変換セルが注目されるようになってきた。しかし、この色素増感太陽電池としては、これまでクロロフィル誘導体やポルフィリンの亜鉛錯体

などが光励起中心としたものが提案されているが、これらは光電変換特性が低いため、太陽電池として実用に供するには、満足しうるものではなかった。

【0004】


【発明が解決しようとする課題】 本発明は、このような事情のもとで、高い光電変換特性を有するポルフィリン誘導体とそれらの金属錯体を用いた、実用化可能な再生型色素増感太陽電池を提供することを目的としてなされたものである。

【0005】

【課題を解決するための手段】 本発明者らは、各種ポルフィリン誘導体の金属錯体を製造し、その光増感作用について種々検討した結果、新規な 5, 10, 15, 20-テトラフェニルポルフィリン又はその誘導体、或はその金属錯体を色素増感太陽電池の色素として用いた場合に、高い光電変換特性を示し、かつ安定した光電流を供給しうる太陽電池が得られることを見出し、この知見に基づいて本発明をなすに至った。

【0006】 すなわち、本発明は、多孔質半導体膜を内側表面に有する透明導電膜を一方の電極とし、金属膜を他方の電極とする電極対間に電解質を介挿し、透明導電膜側から光を照射して両極間に電流回路を形成させる太陽電池において、多孔質半導体膜の細孔中に、一般式

【化 2】



(式中の R は水素原子又は酸性置換基である) で表わされるポルフィリン化合物及びそれらの金属錯体の中から選ばれる少なくとも 1 種の色素を担持させたことを特徴とする色素増感太陽電池を提供するものである。

【0007】

【発明の実施の形態】 次に、添付図面に従って本発明の実施の形態を説明する。図 1 は、本発明太陽電池の構造の 1 例を示すための断面図であって、2 枚の透明基板、例えばガラス基板 1、7 の間に、透明導電膜 2、多孔質半導体膜 3、電解質 5 及び金属膜 6 を順次配置し、かつ前記半導体膜 3 を多孔質に形成して、その細孔中に前記一般式 (1) で表わされるポルフィリン化合物又はその金属錯体が吸着担持されている。また、8 は電流回路、9 はアンメータである。


【0008】 上記の透明導電膜 2 の材料としては、例え

ば酸化スズ、それと酸化インジウムとの複合体が用いられる。また、半導体膜3の材料としては、酸化チタン、酸化亜鉛、酸化タンタルなどが用いられる。この半導体膜3は、多孔質として形成することが必要である。このような多孔質半導体膜を表面に有する半導体膜は、例えば、「ジャーナル・フィジカルケミストリー (J. Phys. Chem.)」, 第94巻, 8720ページ (1990年) に記載されている方法を参考にして、チタンテトライソプロポキシドを2-プロパノールと脱イオン水と硝酸との混合物中に溶かして加水分解して安定な酸化チタンコロイド溶液 (粒子径約8 nm) を調製し、この溶液をTiO₂微粉末 (日本エアロジル社製, 商品名「P-25」) 及びポリエチレングリコールと混合し、この混合物を半導体膜上にスピコートしたのち、500℃以上で焼成することによって製造することができる。

【0009】次に対極として用いる金属膜6の材料としては、アルミニウム、スズ、銀、銅などが用いられるが、特に好ましいのは白金である。この金属膜6は、例えばガラス基板その他の透明基板上に金属を化学蒸着又は物理蒸着することによって形成することができる。

【0010】本発明においては、前記の多孔質半導体膜3の細孔中に、前記一般式(1)で表わされるポルフィリン化合物及びその金属錯体の中から選ばれる少なくとも1種の色素を担持させることが必要である。このポルフィリン化合物の金属錯体としては、例えば一般式

【化3】



(式中のRは水素原子又は酸性置換基、Xはアルコキシ基、アリールオキシ基、アシルオキシ基及びハロゲン原子の中から選ばれる少なくとも1種の配位子、MはMo、Cr、Nb又はWである) で表わされる金属錯体を挙げることができる。この一般式(1)で表わされる金属錯体は文献未載の新規化合物であって、例えば前記一般式(1)で表わされるポルフィリン化合物又はその誘導体に、Mo、Cr、Nb又はWのカルボニル化合物を反応させたのち、一般式HX' (111)

(式中のX'はアルコキシ基、アリールオキシ基、アシルオキシ基又はハロゲン原子である) で表わされる化合

物で処理し、所望に応じ、さらにハロゲン化水素で処理することによって製造することができる。

【0011】この一般式(1)又は(11)で表わされるポルフィリン化合物又はその金属錯体中のRは水素原子又は酸性置換基であるが、この酸性置換基としては、例えばカルボキシ基、スルホン酸残基、スルホン酸塩残基、硫酸残基、硫酸塩残基などがある。また、Mはポルフィリンと錯体を形成しうる金属原子、すなわちMo、Cr、Nb又はWである。

【0012】次にXはMの配位子となる基であって、メトキシ基、エトキシ基、プロポキシ基、ブトキシ基のようなアルコキシ基、フェノキシ基、p-メチルフェノキシ基のようなアリールオキシ基、アセチルオキシ基、プロピオニルオキシ基、グリシルオキシ基のようなアシルオキシ基、フッ素原子、塩素原子、臭素原子のようなハロゲン原子などがある。

【0013】前記一般式(11)で表わされるポルフィリン化合物の金属錯体は、5, 10, 15, 20-テトラフェニルポルフィリン又は5, 10, 15, 20-テトラ置換フェニルポルフィリンのようなポルフィリン化合物に金属カルボニル、例えばモリブデンヘキサカルボニル、クロムペンタカルボニル、ニオブペンタカルボニル、タングステンペンタカルボニルなどを反応させたのち、アルコール、フェノール、カルボン酸と接触させ、さらに所望に応じ、その生成物をハロゲン化水素と接触させて結晶化することにより容易に製造することができる。このポルフィリン化合物と金属カルボニルとの反応は、所望に応じ溶媒、例えばジメチルホルムアミドを用いて行うことができる。この反応は室温において30分ないし2時間という短時間で進行し、65%以上の高い収率でポルフィリン金属錯体が得られ、しかも精製も簡単であるという点で有利である。

【0014】一般式(1)又は(11)で表わされるポルフィリン化合物及びその金属錯体の中から選ばれる少なくとも1種の色素4を多孔質半導体膜3に担持させるには、この色素を適当な溶媒、例えばジメチルホルムアミドに溶解し、この溶液中に多孔質半導体膜を浸せきし、多孔質半導体膜の細孔中に色素が十分に吸着するまで放置したのち、これを取り出し、必要に応じて洗浄後、乾燥する。

【0015】次に、本発明太陽電池において、対極として用いる金属膜6の材料としては、白金が好ましいが、それ以外のアルミニウム、銀、スズ、インジウムなど従来の太陽電池の対極として公知のものも任意に用いることができる。これらの金属膜6は、ガラス基板や酸化インジウム、酸化スズ複合体基板上に、物理蒸着又は化学蒸着することによって形成するのが好ましい。

【0016】本発明太陽電池において、両電極間に介挿される電解質としては、従来太陽電池の電解質として使用されていたものの中から適宜選択して用いることがで

きる。このようなものとしては、例えば前述したグレーツェルらのルテニウムビピリジンカルボン酸色素を用いた太陽電池で用いられている電解質、すなわちヨウ素とヨウ化カリウムを、ポリプロピレンカーボネート25質量%と炭酸エチレン75質量%との混合物からなる媒質に溶解させたものがある。

【0017】本発明太陽電池における透明導電膜2の厚さは0.4~0.6 μ m、好ましくは0.5 μ m、多孔質半導体膜3の厚さは5~30 μ m、好ましくは10~15 μ m、その微粒子サイズは0.01~0.06 μ m、好ましくは0.01~0.03 μ m、金属膜6の厚さは2~20 μ m、好ましくは10~12 μ mの範囲で選ばれる。また両電極間に介挿される電解質の厚さは8~20 μ m、好ましくは10~12 μ mの範囲である。

【0018】このような構造の太陽電池は、両電極間を導線で接続し、電流回路を形成させ、透明導電膜側から420nmの白色光を照射すると2.9%以上の高い光電変換効率で発電することができる。この光電変換効率は、各膜の厚さ、半導体薄膜の状態、色素の吸着量、電解質の種類などに左右されるので、これらの最適条件を選ぶことにより、さらに向上させることができる。

【0019】

【実施例】次に実施例により本発明をさらに詳細に説明する。

【0020】参考例1

5, 10, 15, 20-テトラ(4-カルボキシフェニル)ポルフィリン0.5g(0.6mmol)、モリブデンヘキサカルボニル0.8g(3.2mmol)、乾燥ジメチルホルムアミド100mlの混合物を、窒素雰囲気下で2時間還流させた。この間反応の進行状態を紫外可視スペクトルで追跡した。次いで加熱を停止し、反応混合物を室温まで放冷したのち、溶媒を留去した。次いで残留物をイオン交換カラムクロマトグラフィー処理し、精製し、得られた濃緑色の固体をエチルアルコール中で再結晶することにより、67%の収率で光沢ある結晶を得た。この結晶について、紫外可視スペクトル、赤外吸収スペクトル、ESR、元素分析及び質量スペクトル分析したところ、前記一般式(11)におけるXがエトキシ基、MがMo、Rが酸素原子の構造に該当するポルフィリン金属錯体(D)であることが確認された。また、原料として5, 10, 15, 20-テトラフェニルポルフィリン又は5, 10, 15, 20-テトラ(4-スルホフェニル)ポルフィリンを用い、同様に処理して、前記一般式(11)におけるXがエトキシ基、MがMo、Rがカルボキシル基又はスルホ基の構造に該当するポルフィリン金属錯体(E)及び(F)を得た。

【0021】参考例2

塩化水素を飽和させたヘキサン60ml中に、参考例1で得たポルフィリン金属錯体(E)50mlをエチルアルコール15mlに溶かした溶液を室温で滴下した。生

成した結晶をガラスフィルターでろ取し、ヘキサンで洗浄後、乾燥することにより、82%の収率で白色結晶を得た。このものを紫外可視スペクトル、赤外吸収スペクトル、ESR、元素分析及び質量スペクトル分析したところ、前記一般式(11)におけるXが塩素原子、MがMo、Rがカルボキシル基の構造に該当するポルフィリン金属錯体であることが確認された。

【0022】参考例3

参考例1におけるモリブデンヘキサカルボニルの代りに、クロムヘキサカルボニル、ニオブウムヘキサカルボニル又はタングステンヘキサカルボニルを用い、同じように反応させたところ、それぞれ一般式(11)におけるMがCr、Nb又はWの対応するポルフィリン金属錯体を得られた。

【0023】実施例1

チタントライソプロポキシド62.5mlを2-プロパノール10mlと脱イオン水380mlと濃度70質量%硝酸3mlとの混合物中に溶解し、80℃において8時間加水分解させたのち、蒸発濃縮し、安定な酸化チタンコロイド溶液を調製した。この酸化チタンの粒径は約8nmであった。また、X線回折した結果、この酸化チタンはアナターゼ型であることが分った。厚さ0.5 μ mの酸化インジウム-酸化スズ複合体(以下ITOという)の薄板(25×25nm)の表面に、前記のコロイド溶液10gとTiO₂微粉末(日本エアロジル社製、商品名「P-25」)2gとポリエチレングリコール2gとの混合物をスピンコーティングし、500℃で1時間焼成することにより、厚さ10 μ mの多孔質酸化チタン膜を形成させた。

【0024】5, 10, 15, 20-テトラフェニルポルフィリン(A)、5, 10, 15, 20-テトラ(4-カルボキシフェニル)ポルフィリン(B)、5, 10, 15, 20-テトラ(4-スルホフェニル)ポルフィリン(C)、参考例1で得た5, 10, 15, 20-テトラフェニルポルフィリン金属錯体(D)、5, 10, 15, 20-テトラ(4-カルボキシフェニル)ポルフィリン金属錯体(E)及び5, 10, 15, 20-テトラ(4-スルホフェニル)ポルフィリン金属錯体(F)を5×10⁻⁴mol濃度でジメチルホルムアミドに溶解して調製した溶液中に上記の多孔質酸化チタン膜を浸せきし、80℃において一夜放置したのち、アルゴン雰囲気中に取り出し、メチルアルコールで洗浄し、乾燥した。

【0025】対極として、ITO板(22×25mm)上にスパッタリング法により白金膜(厚さ10 μ m)を設けたものを用い、また電解質として、ヨウ素0.38g及びヨウ化カリウム2.49gの混合物を、プロピレンカーボネート25質量%と炭酸エチレン75質量%との混合物30gに溶解したものを用いて、図1に示す構造の太陽電池を製造した。そのうち、BとCの太陽電池

の性能は次のとおりであった。

【表1】

【0026】

試料	短絡電流 (μA)	開放電圧 (V)	光電変換効率 (%)
B	160	0.44	2.9
C	75	0.38	1.6

【0027】

【発明の効果】本発明により、高い光電変換効率を有し、しかも安定した光電流を供給しうる色素増感太陽電池が提供される。


【図面の簡単な説明】

【図1】 本発明の太陽電池の構造の1例を示す断面図。

【符号の説明】

- 1, 7 透明基板
- 2 透明導電膜
- 3 多孔質半導体膜
- 4 色素
- 5 電解質
- 6 金属膜
- 8 電流回路
- 9 アンメータ

【図1】



フロントページの続き

(72)発明者 安部 英一
佐賀県鳥栖市宿町字野々下807番地1 工業技術院九州工業技術研究所内

(72)発明者 野間 弘昭
佐賀県鳥栖市宿町字野々下807番地1 工業技術院九州工業技術研究所内
Fターム(参考) 5F051 AA14 BA17 FA04 FA19 GA03
5H032 AA06 AS16 CC14 CC16 EE07
EE16 EE17 EE20